



NEROLAC WONDERWOOD CLEAR ACRYLIC LACQUER



PRODUCT DESCRIPTION

Nerolac Wonderwood Clear Acrylic Lacquer is NC free wood lacquer which offers water clear film. It is a unique wood finish which can be applied by brushing or spraying. Nerolac Wonderwood Clear Acrylic Lacquer offers non yellowing and durable coating on all kinds of wood & veneer hence preserves the richness of wooden articles for many years.

PERFORMANCE FEATURES & BENEFITS



Economical



Good Durability



Non Yellowing



Fast Drying

SURFACE PREPARATION

1. Select seasoned wood for coating. If previously coated, remove the coating by scraping or sanding.
2. Sand the surface with emery paper no.180.
3. Apply Nerolac Clear Acrylic Lacquer as a filler coat by spraying viscosity. Allow to air dry 3-4 h.
4. Follow by light sanding with emery paper no.320/400.
5. Wipe off the dust and dirt. Then apply topcoat.
6. Repeat the coat as required depending upon level of filling.

FINISH COAT APPLICATION

1. Adjust the viscosity of Nerolac Clear Acrylic Lacquer for spraying or for brushing by using nerolac NC Thinner. Filter through nylon or muslin cloth and apply as top coat. Apply 2-3 coats of Nerolac Clear Acrylic Lacquer

2. Nerolac Wood Stain 20% max can be used to get the desired color and allow it to dry for 30 minutes.

DISPOSABILITY

Do not pour the leftover sealer down a drain. Seal & keep for disposal. Contains no added Lead, Mercury or Chromium compounds.

METHOD OF APPLICATION: SPRAYING

Recommended Thinner:- Nerolac NC Thinner
Spray Viscosity- 14-16 Secs. On Ford Cup B4 at 30°C.
Spray Pressure- 2-3 kg/cm²
Brushing Viscosity - 50-55 sec on ford cup B4 at 30°C

DRYING TIME AT 30°C

- 1- Touch dry- 20 minutes.
- 2- Sanding Dry - 3-4 h.
- 3 - Hard Dry - Overnight.

HEALTH AND SAFETY INFORMATION

Flash point - above 25°C.
Fire hazard class - flammable.
Health hazard class - harmful, contains volatile organic solvents. Avoid contact.
safety precautions - work in well-ventilated place. Protective hand gloves and eye goggles are recommended.



**Actual coverage may vary depending on method, Condition of Application, Type of Tools, Surface Porosity & Shade. Use of felt Roller may reduce coverage upto 50%.

STORAGE & HANDLING -

Storage- Store in cool and dry place.

Disposal: Do not pour the left overs in the drain or water channel. Dispose off after natural drying.

NOTE

The Container should be tightly closed after use. stir well and filter the base before use.

WEIGHT PER 10L @ 30°C

Nerolac Clear Acrylic Lacquer
Glossy 9.3 +/- kg.

POST APPLICATION INSTRUCTIONS

For the best performance, ensure dry dust-cleaning at regular intervals. Allow a drying-time of 2 weeks for proper film-formation before doing any sponge cleaning with a mild soap-solution or mineral turpentine.

STAIN-CLEANING INSTRUCTIONS

- The paint film needs at least a week after application, to be set & ready for the stain-removal.
- Wipe gently. Do not use liquid bleach.
- For light stains like mud, pencil, tea, coffee etc., use a sponge soaked with soap-solution.
- For tougher stains like pickle, oil, grease, wax & oil crayons etc., use a sponge soaked with mineral turpentine.
- The early removal of stains gives better results.



PACK SIZE

1 L., 4 L., & 20 L.



SHELF LIFE

2 years from the date of manufacturing, when stored in the original tightly closed containers, away from direct sunlight and excessive heat.

DISCLAIMER

The product information and application details given by the company has been provided in good faith and is meant to serve only as a general guideline during usage. The performance claims made are based on the tests carried out under controlled conditions and our past experience with the type of products. Therefore actual performance will depend on local factors prevailing at that point of time. Users are advised to carry-out sample tests by taking trials to ensure the suitability of products for their requirement prior to full-scale usage of our products.

The Company is not liable for factors beyond its control such as application during adverse climatic conditions, use of improper application tools/techniques and surface preparation, any structural defects or the inferior quality of materials other than paints. The warranty/guarantee clauses shall accordingly be amended.